

Production of foam sheets

Abstract

5

- A process for producing foam sheets with a density of from 20 to 200 g·l⁻¹ and with a cross section of at least 50 cm³ by extrusion and foaming of a mixture made from a styrene polymer, from 3 to 15% by weight of a volatile blowing agent and from 0.2 to 10% by weight of graphite particles, based in each case on the styrene polymer, if desired with conventional additives comprises using a volatile blowing agent which is a mixture made of from 95 to 30% by weight of CO₂, from 5 to 70% by weight of H₂O, and from 0 to 60% by weight of a volatile organic compound.

20

25

30

35

40

45